



Superior Sun Protection with

Lam Dyed Films

www.cosmoconsumer.com



INTRODUCTION

Upgrade your windows with Cosmo Sunshield Premium Lam Dyed Charcoal Films, offering long-lasting color, glare reduction, and superior UV protection.

These non-yellowing, scratch-resistant films seamlessly enhance aesthetics while ensuring clear, distortion-free views and better heat rejection for a cooler, more comfortable space.

Benefits:



Uniform
& pleasing
appearance



Good
glare
reduction



Longer resistance
to fading,
bubbling & peeling



Longer
color life



Clear,
distortion-free
visibility



Aesthetic
enhancement



UV
Protection


Lam dyed
Charcoal film

CS-112-SP-CH-05
2Ply 1.5Mil


Solar Properties

Visible Light Transmission	05%
Ultra Violet Rejected	>99%
Infra Red Heat Rejected (780-2500)	20%
Total Solar Energy Rejected	38%
Glare Reduction	94%
Shading Coefficient	0.69
SHGC(G-Value)	0.61

VISIBLE LIGHT TRANSMISSION



SOLAR ENERGY REJECTION




Lam dyed
Charcoal film

CS-112-SP-CH-20
2Ply 1.5Mil


Solar Properties

Visible Light Transmission	20%
Ultra Violet Rejected	>99%
Infra Red Heat Rejected (780-2500)	18%
Total Solar Energy Rejected	32%
Glare Reduction	77%
Shading Coefficient	0.77
SHGC(G-Value)	0.68

VISIBLE LIGHT TRANSMISSION



SOLAR ENERGY REJECTION




Lam dyed
Charcoal film

CS-112-SP-CH-35
2Ply 1.5Mil


Solar Properties

Visible Light Transmission	36%
Ultra Violet Rejected	>99%
Infra Red Heat Rejected (780-2500)	18%
Total Solar Energy Rejected	27%
Glare Reduction	60%
Shading Coefficient	0.82
SHGC(G-Value)	0.73

VISIBLE LIGHT TRANSMISSION



SOLAR ENERGY REJECTION




Lam dyed
Charcoal film

CS-112-SP-CH-50
2Ply 1.5Mil


Solar Properties

Visible Light Transmission	54%
Ultra Violet Rejected	>99%
Infra Red Heat Rejected (780-2500)	18%
Total Solar Energy Rejected	22%
Glare Reduction	40%
Shading Coefficient	0.87
SHGC(G-Value)	0.78

VISIBLE LIGHT TRANSMISSION



SOLAR ENERGY REJECTION




Lam dyed
Charcoal film

CS-112-SP-CH-70
2Ply 1.5Mil


Solar Properties

Visible Light Transmission	69%
Ultra Violet Rejected	>99%
Infra Red Heat Rejected (780-2500)	18%
Total Solar Energy Rejected	18%
Glare Reduction	23%
Shading Coefficient	0.92
SHGC(G-Value)	0.82

VISIBLE LIGHT TRANSMISSION



SOLAR ENERGY REJECTION





Notes



☎ 1800 57 00057



www.cosmoconsumer.com | ✉ sunshield@cosmofilms.com

📍 Regd. Office: 1st Floor, Uppal's Plaza, M-6, Jasola District Centre, New Delhi - 110025